



BluRez CSI50

HYDROPHILIC POLYURETHANE INJECTION RESIN

BluRez CSI50 is a single component polyurethane which reacts with water to form a hydrophilic flexible seal.

Uses

BluRez CSI50 is designed for the sealing/grouting and elastic connection of fissures and cavities in buildings and other civil engineering structures constructed of concrete, brickwork and natural stone. Application uses such as tunnel linings, concrete foundations, subterranean curtains, retaining walls, slab on ground and bridge abutments. Generally, the BluRez CSI50 is most suitable for use in consistently damp or wet environments.

Advantages

- Potable water use approved in accordance with AS/NZ 4020:2005
- Hydrophilic for high water stopping properties
- Easy to use, single pack
- Highly flexible for live structures
- Compatibility with most surfaces
- Rapid foam and gel times

Preparation

Evaluate joint or crack for injection. Drill holes either side of the crack, sloping towards the crack at an angle of approximately 45°, beginning at a distance of 120 - 150 mm from the crack. Insert packer at a depth of approximately 100mm. Pre-injection with water is recommended for priming and facilitation of reaction.

Mixing

BluRez CSI50 is supplied in one component packaging ready for application.

Application

Commence from the widest part of the crack and proceed injecting outwards along the crack in each direction. Turn on pump and slowly increase pressure to a maximum of 30 bar. Stop pumping for every litre injected and allow 1 - 2 minutes for setting. Start and stop injection until the packer will no longer accept material or if the specified pressure has been reached. Move to the next packer and repeat injection process. Continue injection until crack is full and has been adequately sealed. Monitor the effectiveness of the work and allow to settle for 2 - 3 days before returning to site and completing additional injection if required. BluRez CSI50 may be injected into the crack with water at a ratio of 1 : 1.



BluRez CSI50

HYDROPHILIC POLYURETHANE INJECTION RESIN

Product Data

Packaging	20kg kit
Ratio	Single component
Viscosity	800cps @ 25°C
Tensile Strength	2.55MPa
Elongation @ Break	400%
Foaming Factor	3 - 3.5*
Start of Foaming	45 seconds*
Gel Time	55 seconds*
End of Foaming	200 seconds*
Tack Free Time	230 seconds*
Shelf Life	12 months

* Laboratory measurements mixed 1 part water to 3 parts BluRez CSI50 @ 25°C



BluRez CSI50

HYDROPHILIC POLYURETHANE INJECTION RESIN

Contact Bluey

BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia
Ph +61 7 3399 3635 Fax +61 7 3899 9822 brisbane@bluey.com.au

SYDNEY

Bluey Technologies Pty Ltd
Unit 3, 35 Higginbotham Road, Gladesville NSW 2111 Australia
Ph +61 2 9807 2207 sydney@bluey.com.au

MELBOURNE

Bluey Technologies Pty Ltd
PO Box 170, Tullamarine VIC 3043 Australia
Ph +61 3 9826 5570 melbourne@bluey.com.au

PERTH

Bluey Technologies Pty Ltd
Ph +61 402 372 308 perth@bluey.com.au

AUCKLAND

Bluey Technologies
Ph +64 21 102 4797 nz@bluey.com.au

www.bluey.com.au

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative or the contractor is responsible for checking the suitability of products for their intended use. Product properties are dependent upon seasonal and geographical criteria. Product properties and performance may vary between countries and locations within. We recommend that you clarify your specific requirements with your local Bluey representative to ensure that all specific project requirements are met.

NOTE

Field service, where provided, does not constitute supervisory responsibility. Suggestions made by Bluey Technologies Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Bluey Technologies Pty Ltd are responsible for carrying out procedures appropriate to a specific application.

© Bluey Technologies Pty Ltd