

Sikagard®-550 W Elastic

Crack bridging protective coating for concrete

Product Description	<p>Sikagard®-550 W Elastic is a one component, plasto-elastic coating based on UV-curing acrylic dispersion with excellent crack-bridging properties even at temperatures below 0°C.</p> <p>Sikagard®-550 W Elastic complies with the requirements of EN 1504-2 as protective coating.</p>
Uses	<p>Sikagard®-550 W Elastic is used for protection and enhancement of concrete structures (normal and lightweight concrete), especially exposed outdoor concrete surfaces with a risk of cracking</p> <p>Sikagard®-550 W Elastic is used with concrete repair works as an elastic protective coating on Sika® smoothing mortar (refer to your product / system data sheet), fibre cement and overcoating of existing soundly adhering coatings</p> <ul style="list-style-type: none">√ Suitable for protection against ingress (Principle 1, method 1.3 of EN 1504-9),√ Suitable for moisture control (Principle 2, method 2.3 of EN 1504-9)√ Suitable for increasing the resistivity (Principle 8, method 8.3 of EN 1504-9)
Characteristics / Advantages	<ul style="list-style-type: none">■ Crack-bridging even at low temperatures (-20°C)■ High diffusion resistance against CO₂ reducing the rate of carbonation■ Water vapour permeable■ Very good resistance against weathering and ageing■ Environmentally friendly (solvent free)■ Reduced tendency to dirt pick up and contamination
Tests	
Approval / Standards	<p>LPM Report A-33'882-2 dated July 09</p> <p>The product is included in a compilation of tested products and systems as per OS 5a (OS DII) at the German Institute of Road Systems</p>
Product Data	
Form	
Appearance / Colours	Thixotropic liquid available in almost every colour shade.
Packaging	13 litre plastic pail
Storage	
Storage Conditions / Shelf-Life	24 months from date of production if stored properly in undamaged and unopened original sealed packaging in cool and dry conditions. Protect from direct sunlight and frost.
Technical Data	
Chemical Base	Acrylate dispersion
Density	~ 1.39 kg/l (at +20°C)



Solid Volume	~ 53.4%
Solid Content	~ 66.1%
Layer Thickness	Minimum required dry film thickness to achieve the required characteristics (CO ₂ equivalent air thickness of 50 m) ≈ 160 microns. Minimum required dry film thickness to achieve full durability characteristics (CO ₂ diffusion, adhesion after thermal cycling and crack bridging) ≈ 340 microns.

Carbon Dioxide Diffusion Coefficient (μCO₂)

Dry film thickness	d = 160 μm
Equivalent air layer thickness	S _{D, CO₂} = 51 m
Diffusion coefficient CO ₂	μCO ₂ = 3,1 x 10 ⁵
Requirements for protection	S _{D, CO₂} ≥ 50 m

Water Vapour Diffusion Coefficient (μH₂O)

Dry film thickness	d = 230 μm
Equivalent air layer thickness	S _{D, H₂O} = 0.35 m
Diffusion coefficient H ₂ O	μH ₂ O = 1,5 x 10 ³
Requirements for breathability	S _{D, H₂O} ≤ 5 m

VOC Content <40 g / litre

Mechanical / Physical Properties

Elongation at Tear	Elongation at break at room temperature (not exposed to weathering): 120% Elongation at break at -20°C: 70%	
Crack-Bridging Ability	Class A1 (-20°C)	EN 1062-7
Cross Cut	GT 0	EN ISO 2409
Capillary Absorption	w = 0,02 kg/(m ² h ^{0.5})	EN 1062-3
Pull-Off	2,9 (2,8) N/mm ²	EN 1542
Adhesion after Thermal Compatibility	For Outside Application with De-Icing Salt Influence: 2,9 (2,1) N/mm ²	EN 13687-part 1 & part 2
Artificial Weathering	Pass after 2000 hours	EN 1062-11

System Information

System Structure

System	Product ⁽¹⁾	Number of applications
Priming ⁽²⁾	Sikagard [®] -552 W Aquaprimer	1
Top coat ⁽³⁾	Sikagard [®] -550 W Elastic	2 – 3

Note⁽¹⁾

Please refer to the respective data sheet for additional information.

Note⁽²⁾

For very difficult substrate (very dense or weak with tensile strength < 1 N/mm²) and at low temperature, use solvent containing primer Sikagard[®]-551 S Elastic Primer.

Note⁽³⁾

In case of an intensive yellow or red colour shade and/or a dark substrate, more than two coats might be required.

A third coat is also required in order to achieve the required thickness for full durability (crack bridging, adhesion after thermal cycling, etc.)

Application Details

Consumption

Product	Per coat
Sikagard®-551 S Elastic Primer	~ 0.10 - 0.15 kg/m ²
Sikagard®-552 W Aquaprimer	~ 0.10 - 0.15 kg/m ²
Sikagard®-550 W Elastic	~ 0.25 - 0.35 kg/m ²

Substrate Preparation

Exposed concrete without existing coating:

The surface must be dry, sound and free from loose and friable particles. Suitable preparation methods are steam cleaning, high pressure water jetting or blastcleaning.

New concrete must be at least 28 days old.

If required, a levelling pore sealer (e.g. Sika® MonoTop®-620, Sikagard®-720 EpoCem®, etc.) shall be applied – refer to the respective product data sheet. For cement based products, allow a curing time of at least 4 days before coating (except when the EpoCem is used, then coating can be applied after 24 hours with primer).

Exposed concrete with existing coating:

Existing coatings must be tested to confirm their adhesion to the substrate and their suitability - adhesion test average > 0.8 N/mm² with no single value below 0.5 N/mm².

For water based coating, use Sikagard-552 W Aquaprimer as primer.

For solvent based coating, use Sikagard-551 S Elastic Primer as primer.

In case of doubt, carry out adherence testing to determine which primer is most suitable – wait at least 2 weeks prior to conducting the adhesion test - an average value of 0.8 N/mm² is required with no single value below 0.5 N/mm².

Application Conditions / Limitations

Substrate Temperature +8°C min. / +35°C max.

Ambient Temperature +8°C min. / +35°C max.

Relative Air Humidity < 80%

Dew Point Temperature must be at least 3°C above dew point.

Application Instructions

Mixing The materials are supplied ready for use. Stir thoroughly prior to application.

Application Method / Tools Apply Sikagard®-551 S Elastic Primer or Sikagard®-552 W Aquaprimer evenly onto the substrate. For use on very dense substrates up to 10% Sika Thinner C may be added to Sikagard®-551 S Elastic Primer.

Sikagard®-550 W Elastic can be applied by brush, roller or airless spray.

Cleaning of Tools Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.
For Sikagard®-551 S Elastic Primer use Sika® Thinner C.

Waiting Time / Overcoating	Waiting time between coats at +20°C substrate temperature:		
	Previous coating	Waiting time	Next coating
	Sikagard®-552 W Aquaprimer	5 hours min.	Sikagard®-550 W Elastic
	Sikagard®-551 S Elastic Primer	18 hours min.	Sikagard®-550 W Elastic
	Sikagard®-550 W Elastic	8 hours min.	Sikagard®-550 W Elastic
	<p>Note: When application is on existing coatings, the waiting time for both primers will increase by 100%.</p> <p>Refresher coats of Sikagard®-550 W Elastic can be applied without priming if the existing coat has been thoroughly cleaned.</p>		
Notes on Application / Limitations	<p>Do not apply when there is:</p> <ul style="list-style-type: none"> - Expected rain - Relative humidity > 80% - Temperature below +8°C and/or below dew point - Concrete younger than 28 days <p>The system is resistant to aggressive atmospheric influences.</p>		
Curing Details			
Curing Treatment	Sikagard®-550 W Elastic does not require any special curing but must be protected from rain for at least 4 hours at +20°C.		
Applied Product ready for use	Full cure: ~ 7 days at +20°C		
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.		
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.		
Legal Notes	<p>The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Australian version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.</p> <p>PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.</p>		



Sika Australia Pty Limited
 ABN 12 001 342 329

www.sika.com.au
 Tel: 1300 22 33 48

