

Sikasil[®]-Pool

Neutral curing silicone sealant for swimming pools
and permanently wet areas

Product Description	Sikasil [®] -Pool is a one part neutral curing silicone sealant for use in swimming pools and permanently wet areas.
Uses	Sikasil [®] -Pool is suitable for joints in and around swimming pools, areas under permanent water immersion and frequently wet areas, such as shower rooms in sports halls or leisure facilities, between ceramics, tiles, concrete, glass, metals and other typical building substrates, etc.
Characteristics / Advantages	<ul style="list-style-type: none">■ Very high water resistance■ High chlorine resistance (as required in swimming pools due to use of disinfecting solutions)■ Extremely high resistance to fungal attack■ Excellent UV and weathering resistance■ High tear resistance■ Non-corrosive■ High elasticity and flexibility
Product Data	
Colours	White and Transparent – 300ml Cartridges Transparent, Grey and Blue – 600ml Sausages (Grey and Blue only available in Sausages)
Packaging	300ml Cartridges (Carton of 12). 600ml Sausages (Carton of 20)
Storage	
Storage Conditions / Shelf Life	12 months from date of production if stored in undamaged and unopened original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.
Technical Data	
Chemical Base	Oxime silicone, neutral curing
Density	~ 1.05 kg/l (transparent colour) (DIN 53 479)
Skinning Time	~ 5 minutes (+23°C / 50% r.h.)
Curing Rate	~ 2.0 mm/24h (+23°C / 50% r.h.)
Movement Capability	25%

Construction



Sag Flow < 2 mm (DIN EN ISO 7 390)

Service Temperature -40°C to +180°C (Dry conditions)

Mechanical / Physical Properties

Tensile Strength ~ 1.5 N/mm² (+23°C / 50% r.h.) (ISO 8339)

Tear Strength ~ 4.0 N/mm² (+23°C / 50% r.h.) (DIN 24 method C))

Shore A Hardness ~ 20 (after 28 days) (ISO 868)

E-Modulus ~ 0.3 N/mm² at 100% elongation (+23°C / 50% r.h.) (ISO 8339)

Elastic Recovery > 90% (+23°C / 50% r.h.) (ISO 7389)

System Information

Application Details

Consumption

Joint Design:

The joint width must be designed to be within the movement capability of the sealant. Movement joint widths with Sikasil Pool shall be > 10 mm and < 15mm. Sikasil Pool shall not be used in joints of more than 15mm width and a minimum depth or thickness of 6 mm must be applied.

Joint width	10 mm	15mm
Joint depth	8 mm	10mm
Joint length / 300 ml	~ 3.5 m	~2m
Joint length / 600ml	~7.0m	~4m

Substrate Quality

Clean and dry, homogeneous, free from oils and grease, dust and loose or friable particles. Cement laitance must be removed.

Substrate Preparation / Priming

Stainless, steel, PVC, GRP, Stainless steel

Surfaces must be cleaned using a fine abrasive pad followed by Sika Aktivator[®] 205 using a clean towel / cloth. There shall be a 'flash-off' time of at least 15 min.

Concrete, tiles, glazed tiles:

Surfaces must be primed with SikaPrimer[®]-3N using a brush. Before sealing the joint there shall be a 'flash-off' time of at least 30 min. (max. 8 hrs.).

For other substrates please contact the Sika Technical Service Department for advice.

Important note: Primers are only adhesion promoters. They neither substitute for the correct cleaning of the surface nor improve their strength significantly.

Application Conditions / Limitations

Substrate Temperature +5°C min. / +40°C max.

Ambient Temperature +5°C min. / +40°C max.

Substrate Moisture Content Substrates must be dry

Application Instructions

Application Method / Tools

Sikasil®-Pool is supplied ready to use.

After suitable joint and substrate preparation, insert the Backing Rod to the required depth and apply primer if necessary. Insert cartridge into sealant gun and firmly extrude Sikasil®-Pool into the joint making sure that it is in full contact with the side of the joint. Fill the joint and avoid air entrapment. Tool Sikasil®-Pool firmly against the joint sides to ensure good adhesion. Use masking tape where sharp and exact joint lines or exceptionally neat edges are required. Remove the tape whilst the sealant is still soft. Finish the surface of the joint with a suitable smoothing liquid for a perfect sealant surface.

Cleaning of Tools

Clean all tools and application equipment with Sika® Remover 208 / Sika® TopClean-T immediately after use. Remove hardened / cured material mechanically.

Notes on Application / Limitations

Do not use on bituminous substrates, natural rubber, chloroprene, EPDM or on building materials which might bleed oils, plasticizers or solvents.

Do not use in totally confined space because Sikasil®-Pool requires atmospheric moisture to cure.

Do not use Sikasil®-Pool for structural glazing, insulated glazing, food contact applications, or for medical or pharmaceutical use.

Recommendation for use in swimming pools / warm water whirlpools:

Cure Sikasil®-Pool fully before the filling of the pool, minimum 4 days up to 21 days. (dependent on the temperature, ambient humidity and the thickness of the sealant applied). The required vulcanisation or curing time extends with the increasing thickness of the sealant applied.

The resistance of a sealant to chlorine is dependent on the pH value of the water and the amount of free chlorine.

Sikasil®-Pool can be used in swimming pools and warm water whirlpools pools in which the pH value of the water is maintained between 6.5 and 7.6 and the free available chlorine is less than 5 mg/litre.

To reduce the risk of fungal attack of Sikasil®-Pool, the free available chlorine level shall not fall below 0.3 mg/litre in swimming pools and 0.7 mg/litre in warm water whirlpools. Continuous water circulation is required to avoid variable chlorine concentrations in which local chlorine concentrations may fall below these minimum levels. (Note that short term exposure to water with free available chlorine of up to 10 mg/litre can be tolerated).

If there is a very strong smell of chlorine, check the p-H value accordingly.

Regular water circulation is required and must not be interrupted. If interrupted, partial or variable chlorine concentrations arise and may locally fall below the minimum concentration.

Do not use acid based detergents as they increase the danger of fungal attack.

In case of a fungal attack of the sealant must be removed completely when joints are reconstructed.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Construction

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. . In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Australian version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Australia Pty Limited
ABN 12 001 342 329

aus.sika.com
Tel: 1300 22 33 48

