



BluCem HS60 UW

HIGH STRENGTH UNDERWATER GROUT

BluCem HS60 UW is a one component cementitious powder which requires only the addition of water to form an underwater applied cementitious grout.

BluCem HS60 UW has been designed as an anti-washout, highly fluid and self compacting, long pump life product suitable for civil engineering applications. BluCem HS60 UW incorporates advanced superplasticisers and polymers to form a Class C dual shrinkage compensated, high strength and low permeability cementitious grout.

Application Advantages

- Anti-washout
- Highly fluid and self compacting
- Long pump life

Lifecycle Advantages

- Class C dual shrinkage compensated
- High strength
- Low permeability
- Suitable for 100 year design life applications

About the Product

BluCem UW50 is a durable, shrinkage compensated grout which can be placed underwater without washing-out or losing strength. The grout contains special anti-dispersing agents combined with special cements, additives and selected aggregates to produce a versatile and very high performance marine grout. The product can be used in a range of applications where it is not possible to create a dry working environment. BluCem UW50 is a technically advanced marine grade grout which has unique properties in terms of volumetric stability and strength gain with the added benefit of underwater placement capabilities.

Application Solutions

- Pile reinstatement
- Sea walls
- Rock grouting
- Marine repairs
- Undersea void filling

Project Specification Clause

HIGH STRENGTH UNDERWATER GROUT - The underwater applied cementitious grout used for this project shall be a one component cementitious powder which requires only the addition of water to form a non-dispersing underwater applied product. It shall be a pre-blended product that has independent testing to validate the performance outlined in the technical data table on the following pages. BluCem HS60 UW manufactured by Blueey Technologies or equivalent shall be accepted.

Project Examples

Wharf upgrades, new marine structures, port maintenance, tunnels, dams.





BluCem HS60 UW

HIGH STRENGTH UNDERWATER GROUT

Application Specification

CONCRETE PREPARATION

- 1.1 All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications. Host concrete must be roughened and aggregate exposed to ensure good bond. Mechanical chipping or shot blasting of the surface is recommended for this purpose. All surfaces must be free of dust, oils and surface contaminants.

MIXING

- 2.1 Measure and place 80% of the specified volume of potable water to the high shear mixing vessel. Start mixer and slowly add BluCem HS60 UW powder. If powder addition is too fast then large lumps will form and final mix will be slow reaching uniform consistency. Following addition of all powder, mix for 1 - 2 minutes or until uniform consistency then add final 20% of potable water. More or less water may be added within the ratio limits specified on this data sheet.

APPLICATION TEMPERATURES

- 3.1 The mix water's temperature should be kept as low as possible to prevent the grout from hydrating too rapidly.
- 3.2 As with the water temperature, the higher the air temperature the more quickly the grout hydrates and sets. Bluey Technologies specify mixing times and set times at an ambient temperature of 20°C. These times vary with temperature fluctuations, and adjustments will be required to compensate for this. Exposing the pumping hoses to the sun on a hot day accelerates the product's set time. In some cases it may be necessary to cool the material, the mix water, or even the hose itself during the process and pre-planning the storage of all materials to keep the temperature as low as possible.
- 3.3 High-shear mixing can add 1 to 2°C per minute of mixing. In order to minimise this effect, add all ingredients to the mixer as quickly as possible and minimise prolonged batch-mixing procedures.
- 3.4 It is estimated that every 10°C increase in temperature will halve the product set time. Likewise every 10°C reduction will double the set time. These set time variances may have detrimental consequences for the final set product and Bluey Technologies should be consulted where extreme temperatures are anticipated.

PUMPING

- 4.1 Once the grout has been mixed you need an effective pumping method to deliver it to the area of application. Various models of batch mixers and continuous mixers are available for use, all with varying specifications. It is important to match your application's specifics with the capabilities of the mixer and pump. Bluey Technologies are able to recommend the right mixer for your project.
- 4.2 Once the site is ready for grout placement, commence pumping. It is important to pump continuously and avoid the formation of cold joints.
- 4.3 Clean down the machinery and surrounding areas on a regular basis to prevent grout blocking lines and pumps. Following completion, dispose of excess production material in consideration of the environment.

PLACEMENT

- 5.1 The product may be poured or pumped into place. Check formwork for leaks prior to mixing and application of grout. Do not exceed the maximum application thicknesses specified in this data sheet for any wet layer. Best practice in placing underwater grouts is to always have the delivery end of the pump line immersed into the placed grout. This will minimise risk of water infiltration into the grout. Consult Bluey Technologies for further information about aggregate addition for large volume pours.

CURING

- 6.1 No special curing techniques are required.



BluCem HS60 UW

HIGH STRENGTH UNDERWATER GROUT

Product Data

Packaging	20kg, 1000kg, 1200kg bags
Water Addition	2.4 - 3.2 litres per 20kg bag
Yield	10.3 litres per 20kg @ 14% water 10.8 litres per 20kg @ 16% water
Application Thickness	Refer to Bluey Technologies for advice and approval on pour thicknesses with dimensions exceeding 100mm
Pump Life	5 hours @ 20°C
Maximum Particle Size	0.6mm

TESTED CHARACTERISTIC	STANDARD	RESULT
Portland Cement	AS3972	Complies
Aggregates	AS2758.0	Complies
Compressive Strength	AS1478.2 Appendix A	2.8 litres water per 20kg Flowable 8MPa @ 24 hours 45MPa @ 7 days 70MPa @ 28 days 3.2 litres water per 20kg Flowable 5MPa @ 24 hours 35MPa @ 7 days 60MPa @ 28 days
Chloride Ion Content	AS1012.20	<0.03%
Early Volume Change	AS1478.2 Appendix E	1.30%
Change in Height	ASTM C1090	Nil through to 28 days
Flexural Strength	AS1012.11	2.6MPa @ 1 day @ 14% water 7.1MPa @ 7 days @ 14% water 9.3MPa @ 28 days @ 14% water
Setting Time	AS1012.18	Initial set - 825 minutes Final set - 965 minutes
Fresh Wet Density	AS1012.5	2170kg/m ³ @ 16% water
Flow Characteristics	AS 1478.2 Appendix D	600mm @ 14% 710mm @ 16% (Flow Trough)



BluCem HS60 UW

HIGH STRENGTH UNDERWATER GROUT

Contact Bluey

BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia
Ph +61 7 3399 3635 Fax +61 7 3899 9822 brisbane@bluey.com.au

SYDNEY

Bluey Technologies Pty Ltd
Unit 3, 35 Higginbotham Road, Gladesville NSW 2111 Australia
Ph +61 2 9807 2207 sydney@bluey.com.au

MELBOURNE

Bluey Technologies Pty Ltd
PO Box 170, Tullamarine VIC 3043 Australia
Ph +61 3 9826 5570 melbourne@bluey.com.au

PERTH

Bluey Technologies Pty Ltd
Ph +61 402 372 308 perth@bluey.com.au

AUCKLAND

Bluey Technologies
Ph +64 21 102 4797 nz@bluey.com.au

www.bluey.com.au

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative or the contractor is responsible for checking the suitability of products for their intended use. Product properties are dependent upon seasonal and geographical criteria. Product properties and performance may vary between countries and locations within. We recommend that you clarify your specific requirements with your local Bluey representative to ensure that all specific project requirements are met.

NOTE

Field service, where provided, does not constitute supervisory responsibility. Suggestions made by Bluey Technologies Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Bluey Technologies Pty Ltd are responsible for carrying out procedures appropriate to a specific application.

© Bluey Technologies Pty Ltd