

MasterFlow[®] 870

Cementitious high strength non-shrink precision grout

DESCRIPTION

MasterFlow 870 is a non-shrink, natural aggregate precision grout with excellent high early and ultimate strengths. It is specially formulated to provide extended working time even at high ambient temperatures when mixed and placed at any recommended consistency. **MasterFlow 870** is normally placed at a flowable consistency to completely fill voids between 10mm and 100mm.

RECOMMENDED USES

MasterFlow 870 is used for all precision, non-shrink grouting applications with clearances of 10mm to 100mm, including:

- Critical equipment baseplates, soleplates & columns
- Precast wall panels, beams, columns, structural building members and curtain walls
- Patching poured in place concrete structures, e.g. honeycombing, using preplaced aggregate techniques
- Underpinning
- Concrete repair applications where a form and pour material is required
- Applications requiring high early compressive strengths and high ultimate compressive strengths.

FEATURES AND BENEFITS

- **High early strength** – Ensures rapid commissioning of new equipment and structures.
- **High ultimate strength** – Ensures permanence of the installation under static and moderate repetitive loads.
- **Flowable long life grout** – Easy to grout intricate spaces normally inaccessible by conventional grouting technique.
- **Extended working time** – Facilitates grouting of large or difficult placements in a single pour, often without the use of a pump.
- **Dense, non-shrink grout** – Hardens free of bleeding, settlement and drying shrinkage, ensuring tight contact with all grouted surfaces.
- **Easy to use** – Requires no special mixing equipment, it can be mixed in a standard concrete mixer or in a pail using a grout stirrer.
- **No added chloride** – Does not add to chloride load of structure
- **Compliance with codes** – Meets the non-shrink requirements of ASTM C1090 and CRD-C 621, Corps of Engineers Specification for

Non Shrink Grout; provides complete non shrink performance when tested in accordance with simulated Bedplate Technique; tested to the requirements of AS1478.2 "Methods of sampling and testing admixtures for concrete, mortar and grout".

PROPERTIES

Strength development - Typical rates of strength development under variable conditions are as follows:

Effect of consistency on compressive strength (MPa) strength development at 20°C.

Age	Flowable	Plastic
1 day	30	42
3 days	50	61
7 days	65	69
28 days	80	94

Test Method: AS1478.2 Appendix A

Compressive Strength (MPa) effect of temperature on strength development at a flowable consistency

Age	10°C	20°C	30°C
1 day	17	30	33
3 days	45	50	55
7 days	56	65	70
28 days	75	80	85

Test Method: AS1478.2 Appendix A

Flexural Strength (MPa) - effect of temperature on strength development at a flowable consistency.

Age	10°C	20°C	30°C
1 day	3.0	4.5	6.0
3 days	5.0	6.0	7.0
7 days	6.0	7.2	8.1
28 days	7.8	8.6	10.1

Test Method: JIS R 5201

Indirect Tensile Strength (MPa) - effect of temperature on strength development at a flowable consistency

Age	10°C	20°C	30°C
1 day	2.2	2.6	3.0
3 days	2.4	3.1	4.0
7 days	4.1	4.5	5.0
28 days	4.8	6.3	6.5

Test Method: AS1012.10

Volume Change – effect of temperature on volume change at a flowable consistency.

Age	10°C	20°C	30°C
1 day	Positive	Positive	Positive
3 days	Positive	Positive	Positive
7 days	Positive	Positive	Positive
28 days	Positive	Positive	Positive

Test Method: ASTM C1090 (CRD-C621)

MasterFlow[®] 870

Flow Retention – effect of temperature on flow retention at a flowable consistency.

Age	10°C	20°C	30°C
Initial	100%	100%	100%
After 30 minutes	75%	90%	65%
After 1 hour	60%	75%	60%

Bleeding, Plastic Density and Setting Time – effect of temperature on plastic properties at a flowable consistency

Temp.	Bleeding (%)	Plastic Density (kg/m ³)	Setting Time	
			Initial (hours)	Final (hours)
10°C	0	2120	4.6	6.0
20°C	0	2155	4.5	5.2
30°C	0	2245	3.0	4.0

Test Method: Bleeding AS1012.6; Plastic density AS1012.5; Setting time AS1012.18

Water Demand – Actual water demand will depend on consistency required and temperature (both ambient and grout). As a guide, the following table indicates the approximate quantity of water required to mix a 20kg bag of **MasterFlow 870** to various consistencies.

Temperature	Consistency	
	Flowable ¹	Plastic ²
20°C	3.3-3.4 litres	2.6-2.7 litres

¹AS1478.2 Appendix D, 45-55cm lateral flow in the flow trough.
²ASTM C230/C230M, 100-120% flow by flow table after 5 drops in 3 s or AS1478.2 Appendix D, 20-30cm lateral flow in the flow trough.

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

Field and laboratory tests should be conducted on the basis of the desired placing consistency rather than strictly on indicated water demand. If the project requires strength tests be made on site us 50mm cube moulds as indicated in AS 1478.2. do not use cylinder moulds and request a test method from BASF.

VOC content: 6g/L Test method: SCAQMD 304-91

ESTIMATING DATA

One 20 kg bag of **MasterFlow 870** mixed according to directions will yield the following consistency grouts at 20°C:

Flowable – 10.8 litres, approx.

Plastic – 10.4 litres, approx.

APPLICATION

For information about application, please obtain a copy of the BASF “*Application Guide for MasterFlow Cementitious Precision Grouts*” from your local representative. For ‘dry pack’ (damp pack) application, refer to **MasterFlow 700**.

PACKAGING

MasterFlow 870 is packaged in 20kg bags.

SHELF LIFE

MasterFlow 870 has a shelf life of approximately 12 months when stored in a cool dry environment.

PRECAUTIONS

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Safety Data Sheet (SDS) from our office or our website.

MasterFlow-870 ANZ-V2-0915

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product’s suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
 ABN 62008437867
 Level 12
 28 Freshwater Place
 Southbank VIC 3006
Freecall: 1300 227 300
www.master-builders-solutions.basf.com.au

BASF New Zeland Ltd
 Level 4, 4 Leonard Isitt Drive
 Auckland Airport 2022
 Auckland, New Zealand
Freecall: 0800 334 877
www.master-builders-solutions.basf.co.nz

BASF Emergency Advice:
 1800 803 440 within Australia (24hr)
 0800 944 955 within New Zealand